



MasterFormat: 03 63 00

NOVEMBER 2024
(Supersedes May 2011)

REZI-WELD™ 3/2

Epoxy Grout-Patch Kit

DESCRIPTION

REZI-WELD 3/2 grout-patch is a moisture-insensitive, two-component epoxy kit for grouting, sealing base plates, and patching concrete. Part A, the specially formulated epoxy resin and selected, graded aggregates is premixed and packaged in a five-gallon container. A drop-in tray is provided to hold the separately packaged Part B, or activator. This handy, unitized packaging provides its own mixing vessel. Just open the pail, remove the tray, add the activator to the premixed epoxy-aggregate compound and it's ready to use. It's that easy.

REZI-WELD 3/2 grout-patch offers a flowable viscosity for application versatility. It provides a 50-to-60-minute work life and offers high compressive strength. REZI-WELD 3/2 grout-patch resists many industrial chemicals, alkalis, oils, gasoline, most solvents, and some acids.

USES

REZI-WELD 3/2 grout-patch kit is ideal for a variety of construction grouting and patching repair projects. As an epoxy grout, it can be readily poured under base plates or used for anchoring bolts. When applied as a concrete patch, the patching mix serves as a brushed-on primer. The use of a finishing trowel completes the patching application while the primer is still tacky.

FEATURES/BENEFITS

- Ready-to-mix, pre-portioned, unitized package.
- Offers a moisture-insensitive, non-shrink, flowable-viscosity grout.
- Provides fast strength gain and high compressive strength with low heat development.
- Resists corrosion, many industrial chemicals, oils, alkalis, some solvents, fuels, and acids.
- Allows up to 60 minutes of work life.
- Stress and impact resistant.

PACKAGING

5-gallon pail yields approximately 0.50 ft.³ (3.75 gallons) of grout/patch when Part A and Part B are completely mixed together.

SHELF LIFE

Approximately two years in the original, unopened container when stored in a dry environment at temperatures 40° F to 90° F (4° C to 32° C).

TECHNICAL DATA

Compressive Strength @ 73° F (23° C): (ASTM D695)	
1 Day	8,000 psi (55 MPa)
3 Days	11,000 psi (75 MPa)
7 Days	13,000 psi (89 MPa)
Color	Concrete Gray
Flexural Strength @ 7 days (ASTM D790)	4,065 psi (28.05 MPa)
Water Absorption (ASTM D 570) Total Water Absorption, 24 hrs.	0.09%
Bond Strength (ASTM C882 modified) 7 Day Bond Strength to Concrete	4,034 psi (27.84 MPa)

*All technical data is typical information, but may vary due to test methods, conditions and operators.

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • Hampshire, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

APPLICATION

Surface Preparation ... Mechanically abrade all surfaces to be bonded. All surfaces to be bonded must be free of standing water and completely clean of dirt, rust, curing compounds, grease, oil, paint, and unsound materials, which would prevent a solid bond. Vacuum or blow dust away with oil-free, compressed air. Smooth surfaces require abrasive blasting or other mechanical abrasion. Exposed steel surfaces should be abrasive blasted and vacuumed clean; if not possible, degrease the surface and use sandpaper or wire brush to reveal continuous, bright metal.

Mixing... Mix only complete units. Condition all components to 60° F to 85° F (15.6° C to 29.4° C) for 24 hours prior to use. [For maximum flow characteristics, condition REZI-WELD 3/2 to 75° F (23.9° C), prior to use]. Pre-mix each component. Mechanically mix at a slow speed (600-900 rpm) using a drill and Jiffy® Blade or drum mixer for three minutes or until completely mixed while scraping the sides to ensure complete blending of components. The mixed product should be uniform gray in color and not show streaks. Avoid air entrapment. Scrape the sides of the container to ensure complete blending of components. Pot life will decrease as the ambient temperature and/or mass size increases.

Forming ... The flowable consistency of REZI-WELD 3/2 requires that forms be used around the base plates to contain the grout/patch. Seal all forms to prevent the grout/patch from leaking. To prevent adhesion of the grout to the forms, apply a suitable bond breaker. To facilitate placement, allow for a 2" (50.8 mm) formwork head.

Patching ... Prime prepared surface by brushing on REZI-WELD LV STATE from W. R. MEADOWS at a rate of 400 ft.²/gal. (9.8 m²/L). Place patching mix while primer is still tacky with trowel or vibrating screed. Strike off, level, and finish with a finishing trowel.

Application Method ... Avoid air entrapment by pouring the prepared grout into the forms from one or two sides. Maintain a liquid head to ensure complete contact with the base plate. Place enough material to allow the grout to rise slightly above the underside of the base plate. A 1" (25.4 mm) minimum grout head is required.

Cleanup... Tools and equipment should be cleaned immediately after application. Clean equipment away from heat, sparks, and open flame with toluene or xylene. Avoid breathing vapors or allowing epoxy-containing solvent to contact skin. Should skin contact occur, wash thoroughly with soap and water.

PRECAUTIONS

Do not dilute. Addition of solvents will prevent proper curing. Surface temperatures must be between 40° F and 90 °F (4° C to 32° C). As temperature decreases, flow will also decrease. Cold material may need to be pushed, rodded, or chained to achieve proper placement. Keep container tightly closed until ready for use.

HEALTH AND SAFETY

Unused epoxy will generate excessive heat, especially in large quantities. Unused epoxy should be mixed with dry sand in a container to help lower the heat. Refer to Safety Data Sheet for complete health and safety information.

For most recent data sheet, sustainability information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control

over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.